



Anti-Corrosion

BRIGHT COLD GALVANISE

ZINC-RICH BRIGHT PROTECTIVE COATING

A single component, zinc-aluminium coating combining corrosion protection properties with the lustre look of recently galvanized parts. Bright Cold Galvanising Spray is a combination of zinc and aluminium powders, resins and additives, formulated to form a flexible protective film with a bright, glossy appearance.

With unique combination of flexibility and hardness, it provides excellent corrosion and rust resistance to ferrous metals.

Adheres well to metal surfaces and it resists rusting, peeling and fading. Excellent colour match for recently hot-dip galvanized parts. Totally lead and chromate free. No chlorinated solvents.

PRODUCT CODES / FILL SIZES



30292 / 400ml

APPLICATIONS

- Touch-up at Hot-Dip galvanizing plants
- Fences and gates
- Home, garden and farm equipment
- Construction equipment
- Structural steel
- Guard rails
- Welding seams
- Pipes and fittings
- Coastal and shipborne installations
- Repair of LPG storage tanks

DIRECTIONS

- Do not use on energized equipment. Use in well ventilated area.
- Shake aerosol can very well for at least one minute after agitator ball is free. Repeat frequently while using.
- Apply to a clean, degreased, dry surface for best results. Remove rust and scale with a wire brush.
- Apply in light, even coats; best results are obtained with 2 lighter rather than 1 heavy coat.
- Additional coats can be applied after 15-20 minutes.
- When spraying is finished, clean aerosol valve by turning can upside down and press button until only propellant escapes. If clogging occurs, remove button and clean orifice with fine wire.

TECHNICAL DATA (WITHOUT PROPELLANT)

Appearance	Bright Aluminum Finish
Resin Type	Modified Alkyd
Pigment Type	Mixture of Zinc (purity 98%) and Nonleafing Aluminum
Specific Gravity (@ 20°C)	1.06
Flash Point (solvents)	-4°C
Coverage (30 µm, dry)	Approx. 1.6 m ² /can (400 ml)
Application Conditions	
Minimum Ambient Temperature	10°C
Minimum Ambient Temperature	5°C ; 3°C over dew point
Maximum Humidity	85 %RH
Drying Times	30 min
- To Touch	4 h
- To Handle Complete Curing	90% Cured After 7 Days @ 23°C
Recommended Film Thickness	30-40 µm
Thinner / Cleaner	White Spirit, Acetates
Dry film properties (35 µm on degreased metal) Salt spray (ASTM B 117)	100 h (*)
Adhesion on steel (ASTM D 3359)	GT= 0/1
Flexibility (6 mm mandrel, visual)	Pass
Heat resistance (4 h @ 200°C)	Slight Yellowing
Low temperature resistance	-30°C
Hardness Persoz (after 72 h)	80 s

* Typical corrosion protection results will depend mainly on surface conditions and environment. It may be several months up to over 1 year outdoors or more than 2 years indoors. The first application therefore should be checked periodically for signs of corrosion. Once the time of protection under any specific condition is determined, Bright Cold Galvanising Spray may be reapplied at intervals to maintain protection.

MATERIALS COMPATIBILITY

OK	-
CAUTION	-
NOT OK	-

STORAGE & SHELF LIFE

The product may be stored at normal ambient temperatures and has a shelf life of not less than 4 years with correct storage. Aerosols should always be stored below 50°C, away from direct heat and naked flame.

HEALTH AND SAFETY

A separate Safety Data Sheet (SDS) according to EC Regulation 73/404/EEC and 648/2004/EC is available from Ambersil.com or via info.uk@crcind.com

MISREPRESENTATION ACT 1967

TRADE DESCRIPTIONS ACT 1968

The information given in this publication is based on our experience and reports from customers. There are many factors outside our control and knowledge which affect the use and performance of our products and for which reason no warranty is given, express or implied. Users should make their own tests to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the use of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed.

Version 2.0
Created: July 2019
Updated: N/A

CRC Industries UK Ltd.
Wylds Road, Bridgwater
Somerset, TA6 4DD
United Kingdom

t +44 (0)1278 727200
f +44 (0)1278 425644
e sales.uk@crcind.com
w www.ambersil.com

Company Registered No. 04910479

VAT No. GB 821 5195 42

