



Lubricants

## DRY MOLY

### DRY MOLYBDENUM DISULPHIDE LUBRICANT

AMBERSIL DRY MOLY is a resin bonded, high pressure resistant, dry film lubricant containing Molybdenum Disulphide for metal-to-metal lubrication where a wet film cannot be tolerated. Once applied, the MoS<sub>2</sub> lubricant prevents seizing, fretting, scuffing and reduces friction. The thin film also helps prevent corrosion and repels water.

### PRODUCT CODES / FILL SIZES



31576 / 400ml

### APPLICATIONS

Use for the assembly and running in of components to reduce fretting and scuffing where a wet film cannot be used. Apply to threaded and close tolerance components to prevent seizing and aid assembly and disassembly. Particularly effective where high load bearing surface to surface contact is present.

- Mounting of longitudinal press fits (e.g. bolts and bearing seats)
- Assembly of screws and seals
- Surface treatment of rolling and sliding bearings to improve running-in
- Lubrication of guides and joints
- Bearing lubrication for wheel bearings and kiln carts
- Lubrication of open gears
- For use where a wet-film lubricant is undesirable

### DIRECTIONS

- Shake can well (1-2 minutes) until agitator ball is free.
- Ensure application surface is clean, dry, and free from grease, oil and contaminants.
- Hold can upright and spray a thin, even coating from about 25cm away.
- Resin will be touch-dry after 2 - 3 minutes, and ready for use after approximately 2 hours.
- Lightly polish the cured film with a soft, lint-free cloth to improve performance.

## TECHNICAL DATA (WITHOUT PROPELLANT)

Appearance	Thin, opaque black film
Odour	Ketone solvent
Molybdenum Disulphide Content (dry film)	75%
SG @ 20°C	0.620
Pressure @ 25°C	4 bar
Discharge rate	1.1 g/sec
Operating Temp. Range	-150°C to +400°C
Flammability	Classified as Extremely Flammable under current EC Regulations

## MATERIALS COMPATIBILITY

OK	-
CAUTION	-
NOT OK	-

## STORAGE & SHELF LIFE

The product may be stored at normal ambient temperatures and has a shelf life of not less than 6 years with correct storage. Aerosols should always be stored below 50°C, away from direct heat and naked flame.

## HEALTH AND SAFETY

A separate Safety Data Sheet (SDS) according to EC Regulation 73/404/EEC and 648/2004/EC is available from Ambersil.com or via [info.uk@crcind.com](mailto:info.uk@crcind.com)

## MISREPRESENTATION ACT 1967

## TRADE DESCRIPTIONS ACT 1968

The information given in this publication is based on our experience and reports from customers. There are many factors outside our control and knowledge which affect the use and performance of our products and for which reason no warranty is given, express or implied. Users should make their own tests to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the use of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed.

Version 2.0  
Created: July 2019  
Updated: N/A

CRC Industries UK Ltd.  
Wylds Road, Bridgwater  
Somerset, TA6 4DD  
United Kingdom

t +44 (0)1278 727200  
f +44 (0)1278 425644  
e [sales.uk@crcind.com](mailto:sales.uk@crcind.com)  
w [www.ambersil.com](http://www.ambersil.com)

Company Registered No. 04910479

VAT No. GB 821 5195 42

