

CRC 3-36 Special

Ref. : 10033

1. GENERAL DESCRIPTION

Multi-purpose lubricant and corrosion inhibitor.

CRC 3-36 SPECIAL is based on a paraffinic oil and a multiple organic inhibitor system that prevents rust and corrosion by displacing and sealing out moisture and by forming a continuous protection barrier against water and oxygen. The oily, almost invisible film of CRC-3-36 SPECIAL lubricates and penetrates into the finest pores and cracks of the surface. CRC-3-36 SPECIAL's effectiveness for surface protection is derived from three of its principal properties:

- affinity for metal
- low surface tension
- high capillary action.

By its affinity for metal and low surface tension CRC 3-36 SPECIAL displaces moisture and separates it from contact with the metal surface. The high capillary action contributes to the great spreading power.

2. FEATURES

- Multi-purpose lubricant, penetrant and corrosion inhibitor.
- Displaces and seals out moisture, especially after washing or hosing off engines or equipment.
- Penetrates through corrosion to loosen frozen parts.
- Lubricates without leaving a sticky residue.
- Cleans light soils and contaminants.
- Prevents 'fingerprinting' by its protective film.
- Protection of all metals and alloys.
- Compatible with most painted surfaces, coatings, plastics and rubbers.
- Equipped with the 360° (upside-down) spray valve for added convenience.
- Pressurized with non-flammable CO₂ propellant.
- Active product content of 97%.

3. APPLICATIONS


For new, in service or stored equipment

- | | |
|-----------------------------------|---------------|
| • PROCESS MANUFACTURING : | • MACHINING : |
| - Heat treated parts | - Fixtures |
| - Machined surfaces | - Dies |
| - Finished welds | - Jigs |
| - In-process aluminium extrusions | - Shim stock |
| - Precision mechanisms | - Chucks |
| | - Drill rod |



Manufactured by :
CRC Industries Europe NV
Touwslagerstraat 1 – 9240 Zele – Belgium
Tel (32) (0) 52/45.60.11 Fax (32) (0) 52/45.00.34
www.crcind.com





CRC 3-36 Special

Ref. : 10033

- MATERIAL STORAGE
 - Tubings
 - Castings
 - Gears
 - Weld rod and wire
- MAINTENANCE
 - Air actuated tools
 - Conveyors
 - Frozen joints
 - Locks
 - Hoists

4. DIRECTIONS

- Spray in light, even films to lubricate and protect metal surfaces. For electrostatic spraying, addition of polar solvents (butanol, nitropropane, ...) may be necessary.
- Apply liberally and allow to penetrate to free rusted parts. Full penetration may require several hours.
- To displace moisture, spray wet surfaces until run-off is clear and moisture-free.
- To be removed by solvent cleaners (CRC Industrial Degreaser, CRC Fast Dry Degreaser,..) or alkaline degreasing before surface treatment.
- For application of CRC 3-36 SPECIAL in dipping baths, customers should take care to stir from time to time (to distribute small amounts of deposits) and to prevent excessive evaporation of solvent. When stable emulsions have been formed, the bath should be emptied and cleaned, and the product replaced.
- Do not use on energized equipment. Use in a well ventilated area.
- A safety data sheet (MSDS) according EU-Directive 93/112 is available for all CRC products.


5. TYPICAL PRODUCT DATA (without propellant)

Appearance	: light amber
Specific gravity (@ 20°C)	: 0.83
Distillation range of solvents	: 190-250°C
Freezing point	: -50°C
Flash point (open cup)	: 78°C
Dynamic viscosity (@ 20°C)	: 3.9 mPa.s
Ultimate film thickness (@ 20°C, after a 24 hr spread)	: 2.10 ⁻⁶ m.
Maximum expected coverage (@ 20°C, after a 24 hr spread)	: 100 m ² /l.
Solvent dissipation (@ 20°C, thin film)	: 2-4 h.



Manufactured by :
CRC Industries Europe NV
Touwslagerstraat 1 – 9240 Zele – Belgium
Tel (32) (0) 52/45.60.11 Fax (32) (0) 52/45.00.34
www.crcind.com





CRC 3-36 Special

Ref. : 10033

Film properties (after evaporation of solvent)

Dynamic viscosity (@ 20°C)	: 64 mPa.s
Falex true load failure (ASTM D 3233, Proc.A)	: 8900 N
Salt spray resistance (*)	: 65 h.
Heat resistance	: 120°C (150°C short time)

6. PACKAGING

Bulk 200 l

(*) Typical corrosion protection results will depend mainly on surface conditions and indoor environment. It may be less than 1 month or more than 6 months. The first application therefore should be checked periodically for signs of corrosion. Once the time of protection under any specific condition is determined, CRC 3-36 SPECIAL may be re-applied at intervals to maintain protection.

All statements in this publication are based on service experience and/or laboratory testing. Because of the wide variety of equipment and conditions and the unpredictable human factors involved, we recommend that our products be tested on-the-job prior to use. All information is given in good faith but without warranty neither expressed nor implied.

This Technical Data Sheet may already have been revised at this moment for reason such as legislation, availability of components and newly acquired experiences. The latest and only valid version of this Technical Data Sheet will be sent to you upon simple request or can be found on our website: www.crcind.com.

We recommend you to register on this website for this product so you will be able to receive any future updated version automatically.

Version : 10033 03 0801 01
Date : 25 september 2003



Manufactured by :
CRC Industries Europe NV
Touwslagerstraat 1 – 9240 Zele – Belgium
Tel (32) (0) 52/45.60.11 Fax (32) (0) 52/45.00.34
www.crcind.com

